This listing of claims will replace all prior versions, and listings, of claims in the

application:

1. (currently amended) A resin composition <u>devoid of lead and lead alloys</u> for

sliding member, comprising 5 to 30% weight of barium sulfate, 1 to 15% by weight of

magnesium silicate, 1 to 25% by weight of a phosphate, and the balance of a tetrafluoroethylene

resin.

2. (original) A resin composition for sliding member according to claim 1, further

comprising 0.1 to 2% by weight of a solid lubricant as an additional component.

3. (previously presented) A resin composition for sliding member according to claim

1, further comprising 0.1 to 10% by weight of an inorganic filler as an additional component.

4. (original) A resin composition for sliding member according to claim 3, wherein

said inorganic filler is at least one material selected from the group consisting of a potassium

titanate powder, potassium titanate fibers, wollastonite, alumina, silicon carbide and iron oxide.

5. (canceled).

6. (previously presented) A sliding member comprising a steel back plate and a

porous sintered metal layer formed on the steel back plate, wherein pores and surface of the

- 2 -

1380963

YANASE et al. , Appl. No. 10/563,863 September 12, 2008

porous sintered metal layer are respectively filled and coated with the resin composition for sliding member as defined in claim 1.

7. (new) A resin composition devoid of lead and lead alloys for sliding member, comprising 5 to 30% weight of barium sulfate, 1 to 15% by weight of magnesium silicate, 1 to 25% by weight of a phosphate, and 1 to 10% by weight of a low-molecular weight tetrafluoroethylene resin.

8. (new) A sliding member comprising a steel back plate and a porous sintered metal layer formed on the steel back plate, wherein pores and surface of the porous sintered metal layer are respectively filled and coated with the resin composition for sliding member as defined in claim 7.